No. 02/2014.

DECLARATION OF PERFORMANCE

1. Unique identification code of the product-type:

Weldable, ribbed, hot rolled reinforcing steel in bars in steel quality B500SP (PN-H-93220:2006 and MSZ/T 339:2012.03) with R_e ≥ 500 MPa declared yield strength calculated from nominal crosssection, in nominal diameters Ø8, Ø10, Ø12, Ø14, Ø16, Ø18, Ø20, Ø22, Ø25, Ø28 and Ø32 mm

2. Type, batch or serial number or any other element allowing identification of the construction product according to government decree no. 275/2013 (dated 16th July):

Rolling mark applied on the product: 1-17

3. Intended use or uses of the construction product, in accordance with the relevant technical approval, as foreseen by the manufacturer:

The reinforcing steel products may be used as reinforcement of concrete structures according to EN 10080:2005, in steel quality B500SP (PN-H-93220:2006 and MSZ/T 339:2012.03).

The steel bars can be taken into account with the parameters of B 60.50 (MSZ 339:1987) steel by performing diagnostic works on building designed in accordance with standards no. MSZ 15022:1986 and no. MSZ 15022:1986/1M:1992.

The steel bars can be taken into account as product in ductility class C with R_{eH} = 500 MPa declared yield strength calculated from nominal cross-section at design works and strength calculations, according to Annex C of standard no. EN 1992-1-1:2004 + EN 1992-1-1:2004/ AC:2010 (EUROCODE 2).

- 4. Name, registered trade name or registered trade mark and contact address of the manufacturer: CELSA "Huta Ostrowiec" Sp. z.o.o. ul. Samsonowicza 2, PL-27-400 Ostrowiec Świętokrzyski, Poland
- 5. System or systems of assessment and verification of constancy of performance of the construction product: System (1+)
- 6. ÉMI Non-profit Ltd. for Quality Control and Innovation In Building, Diószegi út 37., H-1113 Budapest, Hungary, who issued the Technical Approval no. A-766/2006 is designated body who performed:
 - the determination of product type
 - the audit tests of random chosen samples,
 - the initial inspection of the factory and factory production control,
 - the continuous surveillance, verification and assessment of the factory production control in System (1+), and issued the Certificate of Conformity for the product with no. 138-CPD-12-(C-4/2007)

Essential characteristics	Performance	Applied test and product standards	Technical specification
Yield or proof strength $(R_{eH} \text{ or } R_{p0,2})$	≥ 485 MPa (individual) 500÷625 MPa (characteristic)	MSZ EN 1992-1-1:2010 MSZ EN 10080:2005 MSZ/T 339:2012.03 MSZ 339:1987 PN-H-93220:2006 PN-H-93220:2006 MSZ EN ISO 15630-1:2011 MSZ EN ISO	Technical Approval no. A-766/2006
Tensile strength (R _m)	≥ 582 MPa (individual) ≥ 600 MPa (characteristic)		
Stress ratio (R _m / R _e)	1,13÷1,38 (individual) 1,15÷1,35 (characteristic)		
Elongation (A _{gt})	≥ 6,75% (individual) ≥ 7,5% (characteristic)		
Elongation (A ₅)	≥ 18% (average) ≥ 16% (individual)		
Bendability	180 degrees: d ≤ 16 mm: 3d mandrel d > 16 mm: 6d mandrel		
Tolerances from nominal cross-section	d ≤ 8 mm: ± 6,0% d > 8 mm: ± 4,5%		
Bonding strength (f _R)	8 mm < d ≤ 12 mm: 0.040 d > 12 mm: 0.056	6892-1:2010	
Weldability (C _{eq}):	$C_{\rm eq} \leq 0.52$		
Durability	$C \le 0.24$; $S \le 0.055$; $P \le 0.055$;		
(product analysis):	$N \le 0.014$; $Cu \le 0.85$; $C_{eq} \le 0.52$		
Fatigue:	$\sigma_M = 300 \text{ MPa}; \ 2\sigma_A = 150 \text{ MPa}; $ $n = 2 \cdot 10^6$		

performance in point 7.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4.

Signed for and on behalf of the manufacturer by:

Dyrektor ds. Jakości ZWW

Stanisław Klusek
(signature)

Ostrowiec Świętokrzyski, 04.12.2013

(Stanisław Klusek)

(Quality Manager of RPP)

8. The performance of the product identified in points 1 and 2 is in conformity with the declared